

Anhydrous Makeup

Contains REACT-NTI products (highlighted in red)

Formulary

Ingredients	% Wt.
<i>Phase A</i>	
Permethyl 102A (Presperse) (isoeicosane)	37.20
Carnauba wax	3.50
EnviroPure 301-310 (React-NTI)	1.00
Propylparaben USP (ISP) (propylparaben)	0.20
<i>Phase B</i>	
Sericite PHN (Presperse) (mica)	30.00
SP-29 UVS (Presperse) (bismuth oxychloride (and) silica (and) mica)	3.00
Farona I-III (React-NTI)	3.00
Titanium Dioxide 3328 (Whittaker) (titanium dioxide)	7.00
Red Iron Oxide 7080 (Warner Jenkinson) (iron oxide)	0.80
Yellow Iron Oxide 7055 (Warner Jenkinson) (iron oxide)	0.60
Black Iron Oxide 7133 (Warner Jenkinson)	0.30
<i>Phase C</i>	
Amisol (Lucas Meyer) (lecithin (and) polysorbate 20 (and) sorbitan lauryl)	0.40
<i>Procedure</i>	
1.	In a suitable vessel, combine all ingredients of Phase A and heat to 82°C under Lightnin-type mixing.
2.	In a separate vessel, combine Phase B in a ribbon-type blender to even dispersion.
3.	Add Phase B to Phase A under Lightnin-type mixing; mix to uniformity.
4.	Add Phase C and continue mixing.
5.	Pour into appropriate containers at 70-75°C.



REACT-NTI, LLC

6680 North Highway 49, Lino Lakes, MN 55014

Phone: (651) 217-2138 Fax: (651) 784-2902

www.react-nti.com

Note: The statements made herein are based on our research and the research of others, and are believed to be accurate. No guarantee of their accuracy is made, however, and the products discussed are sold without warranty, expressed or implied, including warranty of merchantability and fitness for use of this material, and upon condition that purchasers shall make their own tests to determine the suitability of such products for the particular purposes. The user assumes all risk of use or handling, whether or not in accordance with any statements of the supplier. Supplier's liability, if any, for any action arising out of the material being supplied shall be limited to replacement of material. Statements concerning the possible use of these products are not intended as recommendations to use these products in infringement of any patent.