

Instant Polish

Contains REACT-NTI products (highlighted in red)

Formulary

Ingredients	% Wt.
<i>Phase A</i>	
Exxsol D40 (ExxonMobil)	23.00
DC 200 Fluid, 350 cSt (Dow Corning)	1.40
DC 200 Fluid, 1,000 cSt (Dow Corning)	1.00
DC 5200 Formulation Aid (Dow Corning)	2.00
EnviroPure 301-310 (React-NTI)	1.00
Farona I-III (React-NTI)	1.00
<i>Phase B</i>	
Water	57.60
Sillikolloid P.87 (Hoffmann Minerals)	8.50
Wax emulsion (35% active blend of soft/hard waxes)	3.00
50% sodium citrate in water	2.00
<i>Procedure</i>	
1.	Blend Phase A ingredients in the main vessel under low shear.
2.	In an auxiliary vessel, load Phase B ingredients in the order listed. Mix with low shear.
3.	Add Phase B to Phase A very slowly under high shear until the emulsion begins to form.
4.	The remainder of Phase B can then be added at a faster rate.
5.	When addition is complete, mix with high shear.



REACT-NTI, LLC

6680 North Highway 49, Lino Lakes, MN 55014

Phone: (651) 217-2138 Fax: (651) 784-2902

www.react-nti.com

Note: The statements made herein are based on our research and the research of others, and are believed to be accurate. No guarantee of their accuracy is made, however, and the products discussed are sold without warranty, expressed or implied, including warranty of merchantability and fitness for use of this material, and upon condition that purchasers shall make their own tests to determine the suitability of such products for the particular purposes. The user assumes all risk of use or handling, whether or not in accordance with any statements of the supplier. Supplier's liability, if any, for any action arising out of the material being supplied shall be limited to replacement of material. Statements concerning the possible use of these products are not intended as recommendations to use these products in infringement of any patent.