

# Liquid Powder Makeup

Contains REACT-NTI products (highlighted in red)

## Formulary

Ingredients	% Wt.
<b>Phase A</b>	
Estol 1543 (Uniqema) (octyl palmitate)	18.54
Eutanol G (Cognis) (octyldodecanol)	15.54
Crodamol IPM (Croda) (isopropyl myristate)	12.36
Softisan 100 (Hüls America) (hydrogenated coco-glyceride)	10.30
Candelilla Wax (Koster Keunen) (candelilla (euphorbia cerifera) wax)	5.30
<b>EnviroPure 301-310 (React-NTI)</b>	<b>3.00</b>
Carnauba Wax (Koster Keunen) (carnauba (copernicia cerifera) wax)	1.03
309-E Magnesium Carbonate (Whittaker, Clark and Daniels) (magnesium carbonate)	1.03
Vitamin E Acetate-C (BASF) (tocopheryl acetate)	0.51
DC 200 (350cst) (Dow Corning) (dimethicone)	0.51
Propylparaben	0.10
<b>Phase B</b>	
7055 Yellow (Warner Jenkinson) (iron oxides)	0.25
7051 Red (Warner Jenkinson) (iron oxides)	0.25
7061 Brown (Warner Jenkinson) (iron oxides)	0.04
7133 Black (Warner Jenkinson) (iron oxides)	0.02
Dry-Flo Elite LL (National Starch) (aluminum starch (and) octenylsuccinate (and) lauroyl lysine)	18.00
<b>Farona I (React-NTI)</b>	<b>2.00</b>
09985 AW TiO2 (Warner Jenkinson) (titanium dioxide)	10.82
Cab-O-Sil M5 (Cabot) (silica)	0.25
Methylparaben	0.15
<b>Procedure</b>	
1.	Combine Phase A ingredients; heat to 80°C.
2.	Blend Phase B ingredients until uniform.
3.	Sift Phase B into Phase A at 80°C slowly; mix thoroughly at slow speed.
4.	Cool to 70°C.
5.	Pour into pans.
6.	Cool at room temperature.



## REACT-NTI, LLC

6680 North Highway 49, Lino Lakes, MN 55014

Phone: (651) 217-2138 Fax: (651) 784-2902

[www.react-nti.com](http://www.react-nti.com)

Note: The statements made herein are based on our research and the research of others, and are believed to be accurate. No guarantee of their accuracy is made, however, and the products discussed are sold without warranty, expressed or implied, including warranty of merchantability and fitness for use of this material, and upon condition that purchasers shall make their own tests to determine the suitability of such products for the particular purposes. The user assumes all risk of use or handling, whether or not in accordance with any statements of the supplier. Supplier's liability, if any, for any action arising out of the material being supplied shall be limited to replacement of material. Statements concerning the possible use of these products are not intended as recommendations to use these products in infringement of any patent.