

Relaxing Hair Balm and Defrizzer

Contains REACT-NTI products (highlighted in red)

Formulary

Ingredients	% Wt.
Phase A	
Deionized water	53.60
Carbopol Ultrez 21 Polymer (Noveon) (acrylates/C10-30 alkyl crosspolymer)	1.00
Propylene glycol	3.00
EnviroPure 301-310 (React-NTI)	3.00
Farona I-III (React-NTI)	3.00
Pelemol DIA (Phoenix) (diisopropyl adipate)	3.00
Crodamol ICS (Croda) (isocetyl stearate)	5.00
244 Fluid (Dow Corning) (cyclomethicone)	1.00
Glydant (Lonza) (DMDM hydantoin)	0.20
AMP-95 (Dow) (aminomethylpropanol)	1.00
Phase B	
Deionized water	18.80
Fixate G-100 Polymer (Noveon) (AMP-acrylates/allyl methacrylate copolymer 26%)	7.40
Procedure	
1.	Sprinkle Carbopol Ultrez 21 Polymer on surface of deionized water; allow to self-wet.
2.	Begin agitation.
3.	Add items two through seven, mixing well after each addition.
4.	Neutralize with AMP-95.
5.	Pre-mix Phase B and slowly add to main batch with high-speed mixing.



REACT-NTI, LLC

6680 North Highway 49, Lino Lakes, MN 55014

Phone: (651) 217-2138 Fax: (651) 784-2902

www.react-nti.com

Note: The statements made herein are based on our research and the research of others, and are believed to be accurate. No guarantee of their accuracy is made, however, and the products discussed are sold without warranty, expressed or implied, including warranty of merchantability and fitness for use of this material, and upon condition that purchasers shall make their own tests to determine the suitability of such products for the particular purposes. The user assumes all risk of use or handling, whether or not in accordance with any statements of the supplier. Supplier's liability, if any, for any action arising out of the material being supplied shall be limited to replacement of material. Statements concerning the possible use of these products are not intended as recommendations to use these products in infringement of any patent.