

Soft Pressed Powder

Contains REACT-NTI products (highlighted in red)

Formulary

Ingredients	% Wt.
<i>Phase A</i>	
Boron Nitride TBN12 (Saint-Gobain) (boron nitride (and) perfluoroperhydrophenanthrene)	32.00
Sunsil 130 (Sunjin) (silica)	13.00
Coulourmat PL Red (Creations Couleurs) (mica (and) hydrogenated polydecen (and) hydrogenated lecithin (and) iron oxide)	1.20
Coulourmat PL Yellow (Creations Couleurs) (mica (and) hydrogenated polydecen (and) hydrogenated lecithin (and) iron oxide)	0.38
Coulourmat PL Black (Creations Couleurs) (mica (and) hydrogenated polydecen (and) hydrogenated lecithin (and) iron oxide)	0.12
Micapoly 320 B (Creations Couleurs) (mica (and) hydrogenated lecithin)	12.30
Farona I-III (React-NTI)	10.00
<i>Phase B</i>	
Tefpoly Pur WL3 (Creations Couleurs) (PTFE)	2.00
<i>Phase C</i>	
Nylonpoly WL8 (Creations Couleurs) (nylon-12)	23.00
<i>Phase D</i>	
Creasil IH CG (C.I.T. Sarl) (isohexadecane)	4.00
<i>Phase E</i>	
Fiflow pb 220 (Novallia) (perfluoroperhydrophenanthrene)	1.00
<i>Procedure</i>	
1.	Mix Phase A ingredients together until completely and thoroughly dispersed.
2.	Add Phase B and Phase C.
3.	Add binder Phase D and Phase E together and disperse and coat powder materials.
4.	Press on a Vetraco between 15 and 45 bars pressure depending upon end use (i.e. blush or eye-shadow).



REACT-NTI, LLC

6680 North Highway 49, Lino Lakes, MN 55014

Phone: (651) 217-2138 Fax: (651) 784-2902

www.react-nti.com

Note: The statements made herein are based on our research and the research of others, and are believed to be accurate. No guarantee of their accuracy is made, however, and the products discussed are sold without warranty, expressed or implied, including warranty of merchantability and fitness for use of this material, and upon condition that purchasers shall make their own tests to determine the suitability of such products for the particular purposes. The user assumes all risk of use or handling, whether or not in accordance with any statements of the supplier. Supplier's liability, if any, for any action arising out of the material being supplied shall be limited to replacement of material. Statements concerning the possible use of these products are not intended as recommendations to use these products in infringement of any patent.